

90 Dayton Avenue Suite 6E Passaic, New Jersey 07055


Tel +1 973-928-8300 www.mwt-materials.com

MAC-2200-WP

RF Isolation Fabric

MAC-2200-OC

RF Isolation Fabric with Outer Cover



MAC-2200-WP is a simple solution for effective RF signal attenuation in many commercial applications. It provides — 100 dB RF isolation from 100 MHz to 1 GHz and more than - 85 dB to 18GHz. Very light, thin, flexible, wear and tear resistant, it can be applied directly to studs, standard sheetrock and other structures using simple and inexpensive methods. The product is well suited to both new and retrofit construction. It provides a good degree of isolation typically seen with metal sheathing. It offers

significant savings in labor, shipping and construction costs and needs virtually no physical space unlike competitive materials.

MAC-2200-WP does not require specialized tools or techniques to apply. This flexible product comes in rolls. Special shapes can be fabricated for custom applications. It can be modified to your specific requirements.

Typical applications:

- Security uses, including RF shielding to prevent the use of cellular telephones and other communication devices (including covert ones) in selected areas.
- Construction of RF quiet zones for scientific and developmental research.
- Isolation of noisy RF sources to protect sensors and receivers.
- Isolation of cell tower transmitters to protect building inhabitants.
- Extraneous Artifact Reduction in MRI and other High RF Flux Applications.
- Medical uses, including RF shielding for hospital instrumentation, and Intensive Care Units.
- Wideband EMI Shielding.

FEATURES:

Construction:

MAC-2200-WP is a single layer flexible panel consisting of isolation ground plane material.

MAC-2200-OC is the above material with an acrylic nylon pack cloth outer cover and is manufactured to the customer's size and shape requirements. It is available in standard black or grey. It can be waterproofed for outdoor applications. Grommets or D rings can be added at customer request.



90 Dayton Avenue Suite 6E Passaic, New Jersey 07055

Tel +1 973-928-8300 www.mwt-materials.com

Size:

MAC-2200-WP Typically supplied in rolls of 52 in minimum (132 cm). It can be cut to customer size requirements.

MAC-2200-OC is made to order as per customer requirements and should not be cut.

Color:

MAC-2200-WP is copper colored on both sides.

Mechanical properties:

Substrate Rip stop Nylon

Metal Nickel over Silver

Basis Weight 12-14 oz. /yard²

Thickness 0.05 in (0.0127 cm)

Weight Typically less than 0.1 lbs./ft² (0.45 kg/m²)

Thermal Stability Range of -40°F to 160°F Elongation MD 9% (per AST< D5035

Tensile Strength 7.5 /18.5 lb. /in (CMD / MD)

Hazardous Material None

Visual Defects: Uniform surface texture and appearance

Thermal Cycles: 10 cycles, 1 hr/-20°F - 1 hr/70° F, no adverse effects

Low Temperature Impact: -20°F, 1.5 ft. lbs., and no adverse effects

Effects of Liquids Oil: No adverse effects after 1000 hours (ASTM-B-117)
Effects of Liquids, Water: Less than 6% increase in volume (ASTM-D-471)

Performance:

-100 dB RF isolation from 100 MHz to 1 GHz

Greater than -85 dB RF isolation from 1 GHz to over 18 GHz

Nail, screw and staple punctures have no effect on signal attenuation

Page 2 MWT TDS MAC-2200 Ver 3.0